



UNIVERSITI PUTRA MALAYSIA

**VARIATION AND RELATIONSHIP OF SELECTED WOOD
PROPERTIES IN PLANTED KELEMPAYAN
(NEOLAMARCKIA CADAMBA (ROXB.) BOSSER)**

ISMAIL JUSOH

FH 1993 2

VARIATION AND RELATIONSHIP OF SELECTED WOOD
PROPERTIES IN PLANTED KELEMPAYAN
(*Neolamarckia cadamba* (Roxb.) Bosser)

By

ISMAIL JUSOH

Thesis Submitted in Fulfillment of the Requirements for
the Degree of Master of Science in the Faculty of
Forestry, Universiti Pertanian Malaysia

July 1993



ACKNOWLEDGMENTS

Most sincere and special thanks are due to my chairman Assoc. Prof. Mohd. Zin Jusoh for his invaluable time, advice, guidance and suggestions which made the successful completion of this study possible. My thanks are also due to Assoc. Prof. Dr. Razali Abd. Kader and Tuan Hj. Hamami Sahri for the advice, suggestions and discussion during the preparation of the manuscript. Grateful thanks also due to Assoc. Prof. Dr. Yusuf Hadi and Dr. Mohd. Zamin Jumaat for their help and comments.

I thank the Faculty of Forestry for providing fund for this study under the IRPA programme. Acknowledgment is also extended to Encik Shaharuddin Mohd. Ismail the State Director, Department of Forestry Negeri Sembilan/Melaka for providing the material used in this study and to Forest Research Institute Malaysia (FRIM) for making available much of the equipment used to cut the material.

Special thanks and appreciations are due to all staff of Faculty of Forestry especially from the Department of Forest Production for their invaluable assistance in carrying out this investigation.

Last but not least I am most grateful to my wife Salviah and daughter Afiqah for their patience and encouragement in all phases of this study.

TABLE OF CONTENTS

	Page
ACKNOWLEDGMENTS	ii
LIST OF TABLES	viii
LIST OF FIGURES	xiii
LIST OF PLATES	xv
LIST OF ABBREVIATIONS	xvi
ABSTRACT	xvii
ABSTRAK	xix
CHAPTER	
I INTRODUCTION	1
Problem Statement	1
Objectives.....	3
II LITERATURE REVIEW	5
Nomenclature	5
Occurrence and Distribution	7
Physical Properties	9
Gross Features	9
Density and Specific Gravity	9
Moisture Content and Shrinkage	12
Static Bending	14
Anatomical Properties	15
Vessel	15
Fibres	17
Rays	20
Quantification of Wood Anatomy	21
Semi-automatic Image Processor	21



	Automatic Image Processor (Analyzer)	23
III	MATERIALS AND METHODS	26
	The Stand and Trees	26
	Field Sampling	27
	Determination of Specific Gravity, Moisture Content and Shrinkage	30
	Sample Preparation	30
	Specific Gravity Determination	31
	Moisture Content Determination	32
	Shrinkage Determination	32
	Preparation of Static Bending Test Specimens	33
	Drying	34
	Static Bending Test	34
	Preparation of Specimen for Anatomical Properties	35
	Preparation of Cubes for Sectioning	35
	Cubes Waterlogging	36
	Sectioning	36
	Staining	36
	Mounting	37
	Quantification of Wood Anatomical Characteristics Using the Image Analysis System	38
	Wood Tissue Proportions	39
	Fibre Characteristics	45
	Vessel Diameter	48
	Preparation of Specimen from Bending Test After Failure for Relationship Study	48
	Analysis of Results	49



	General Properties of Wood	49
	Analysis of Variance	50
	Correlation Analysis	51
	Regression Analysis	51
	Statistical Method	52
IV	RESULTS AND DISCUSSION	53
	General Properties	53
	Physical Properties	53
	Mechanical Properties	55
	Tissue Proportions	56
	Fibre and Vessel Characteristics	57
	Between-tree Variations	59
	Physical Properties	59
	Mechanical Properties	62
	Tissue Proportions	64
	Fibre Characteristics and Vessel Diameter	66
	Within-tree Variations	69
	Physical Properties	69
	Mechanical Properties	84
	Tissue Proportions	8
	Fibre Characteristics and Vessel Diameter	95
	Correlation Analysis	103
	Physical Properties	103
	Tissue Proportions	105
	Fibre Characteristics	108
	Regression Analysis	109

	Relationship between Specific and Anatomical Properties	109
	Relationship between Mechanical Properties and Specific gravity and Anatomical Properties	112
V	SUMMARY AND RECOMMENDATIONS	117
	Summary	117
	Recommendations	120
	LITERATURE CITED	121
	APPENDIX	
A	Additional Tables	128
	VITA	162



LIST OF TABLES

Table	Page
1 Density and Specific Gravity of Kelempayan	10
2 Characteristics of the Sampled Trees of Kelempayan	27
3 Some Physical Properties of Kelempayan	54
4 Modulus of Elasticity and Modulus of Rupture of Kelempayan	56
5 Tissue Proportions of Kelempayan	57
6 Fibre and Vessel Characteristics of Kelempayan	58
7 Summary of Analysis of Variance for Physical Properties	60
8 Tree Differences of Physical Properties	60
9 Summary of Analysis of Variance for Modulus of Elasticity and Modulus of Rupture	63
10 Tree Differences of Bending Strength	63
11 Summary of Analysis of Variance for Wood Tissue Proportions	64
12 Tree Differences of Tissue Proportions	64
13 Summary of Analysis of Variance for Fibre Characteristics and Vessel Diameter	67
14 Tree Differences in Fibre Characteristics and Vessel Diameter	67
15 Height Differences of Physical Properties	69
16 Radial Differences of Physical Properties	70
17 Bolt Positions Differences of Bending Strength	84
18 Radial Positions Differences of Bending Strength	85
19 Height Levels Differences of Tissue Proportions	88



20	Radial Positions Differences of Tissue Proportions	88
21	Height Differences of Fibre Characteristics	96
22	Radial Differences of Fibre Characteristics and Vessel Diameter	96
23	Correlation Coefficient and Probability of Significance Level Among Physical Properties	103
24	Correlation Coefficient and Probability of Significance Among Wood Tissues	105
25	Correlation Coefficient and Probability of Significance for Fibre Characteristics	108
26	Linear Regressions of Specific Gravity on Anatomical Properties	110
27	Linear Regressions of Modulus of Elasticity on Specific Gravity and Anatomical Properties	112
28	Linear Regressions of Modulus of Rupture on Specific Gravity and Anatomical Properties	113
29	Average Physical Properties Values of Each Tree at Five Height Positions and Three Wood Types	129
30	Average Mechanical Properties of Each Tree at Three Different Bolts and Wood Types	131
31	Average Tissue Proportions Values of Each Tree at Five Height Levels and Three Wood Types	133
32	Average Fibre Length, Lumen Diameter, Wall Thickness and Vessel Diameter of Each Tree at Five Height Levels and Three Wood Types	135
33	Mechanical, Physical and Anatomical Properties of Corresponding Static Bending Specimen Used for Regression Analyses	137
34	Analysis of Variance for Specific Gravity	139
35	Analysis of Variance for Green Moisture Content	139
36	Analysis of Variance for Tangential Shrinkage	139
37	Analysis of Variance for Radial Shrinkage	140

38	Analysis of Variance for Longitudinal Shrinkage	140
39	Analysis of Variance for Volumetric Shrinkage	140
40	Analysis of Variance for Modulus of Elasticity	141
41	Analysis of Variance for Modulus of Rupture	141
42	Analysis of Variance for Cell Wall Proportion	141
43	Analysis of Variance for Lumen Proportion	142
44	Analysis of Variance for Vessel Proportion	142
45	Analysis of Variance for Ray Proportion	142
46	Analysis of Variance for Fibre Proportion	143
47	Analysis of Variance for Fibre Length	143
48	Analysis of Variance for Fibre Diameter	143
49	Analysis of Variance for Fibre Lumen Diameter	144
50	Analysis of Variance for Fibre Wall Thickness	144
51	Analysis of Variance for Vessel Diameter	144
52	Best One Variable of Maximum R-Square Improvement for Dependent Variable Specific Gravity	145
53	Best Two Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	145
54	Best Three Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	146
55	Best Three Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	146
56	Best Four Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	147

57	Best Five Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	147
58	Best Six Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	148
59	Best Seven Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	148
60	Best Eight Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	149
61	Best Nine Variables of Maximum R-Square Improvement for Dependent Variable Specific Gravity	149
62	Best One Variable of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	150
63	Best Two Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	150
64	Best Three Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	151
65	Best Four Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	151
66	Best Five Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	152
67	Best Six Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	152
68	Best Seven Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	153
69	Best Seven Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity	153
70	Best Eight Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	154

71	Best Nine Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	154
72	Best Nine Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	155
73	Best Ten Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Elasticity (MOE)	155
74	Best One Variable of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	156
75	Best Two Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	156
76	Best Three Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	157
77	Best Four Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	157
78	Best Five Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	158
79	Best Six Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	158
80	Best Seven Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	159
81	Best Seven Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	159
82	Best Eight Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	160
83	Best Nine Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	160
84	Best Ten Variables of Maximum R-Square Improvement for Dependent Variable Modulus of Rupture (MOR)	161



LIST OF FIGURES

Figure		Page
1	Sampling Scheme for Cross-sectional Discs and Bolts for the Sampled Trees	29
2	The Sampling of Bolt for Mechanical Properties	33
3	Sampling for Cubes from Discs	35
4	Position of Sections	38
5	The Sampling Fields for Wood Tissues	40
6	Sequence of Operations Performed for Tissue Proportion Measurement	44
7	Scheme for the Determination of Specific Gravity and Anatomical Properties from Bending Specimen Failure	49
8a	Vertical Variation in Overall Mean of Specific Gravity	71
8b	Radial Variation in Overall Mean of Specific Gravity	72
9a	Vertical Variation in Overall Mean of Green Moisture Content	76
9b	Radial Variation in Overall Mean of Green Moisture Content	77
10	Vertical Variation in Overall Mean of Tangential Shrinkage	78
11	Radial Variation in Overall Mean of Radial Shrinkage	79
12	Radial Variation in Overall Mean of Longitudinal Shrinkage	81
13a	Vertical Variation in Overall Mean of Volumetric Shrinkage	82
13b	Radial Variation in Overall Mean of Volumetric Shrinkage	83
14a	Vertical Variation in Overall Mean of Modulus of Elasticity	85
14b	Vertical Variation in Overall Mean of Modulus of Rupture	86

15a	Radial Variation in Overall Mean of Modulus of Elasticity	87
15b	Radial Variation in Overall Mean of Modulus of Rupture	87
16a	Vertical Variation in Overall Mean of Vessel Proportion	89
16b	Radial Variation in Overall Mean of Vessel Proportion	90
17a	Vertical Variation in Overall Mean of Ray Proportion	91
17b	Radial Variation in Overall Mean of Ray Proportion	92
18	Radial Variation in Overall Mean of Cell Wall Proportion	93
19	Radial Variation in Overall Mean of Lumen Proportion	94
20	Radial Variation in Overall Mean of Fibre Proportion	95
21a	Vertical Variation in Overall Mean of Fibre Length	97
21b	Radial Variation in Overall Mean of Fibre Proportion	98
22a	Vertical Variation in Overall Mean of Fibre Diameter	99
22b	Vertical Variation in Overall Mean of Fibre Lumen Diameter	99
23a	Radial Variation in Overall Mean of Fibre Diameter	100
23b	Radial Variation in Overall Mean of Fibre Lumen Diameter	101
24	Radial Variation in Overall Mean of Fibre Wall Thickness	102
25	Radial Variation in Overall Mean of Vessel Diameter	102

LIST OF PLATES

Plate	Page
1 Determination of Cell Wall Proportion (magn. x100)	41
2 Determination of Ray Proportion (magn. x100)	42
3 Determination of Vessel Proportion (magn. x100)	43
4 Fibre Length Measurement (magn. x40)	45
5 Fibre Diameter and Fibre Lumen Diameter Measurement (magn. x400)	46



LIST OF ABBREVIATIONS

SG	- Specific Gravity
GMC	- Green Moisture Content
MC	- Moisture Content
ST	- Tangential Shrinkage
SR	- Radial Shrinkage
SL	- Longitudinal Shrinkage
SV	- Volumetric Shrinkage
MPa	- Megapascal
μm	- Micron(s)
MOE	- Modulus of Elasticity
MOR	- Modulus of Rupture
SAS	- Statistical Analysis System
ANOVA	- Analysis of Variance
LSD	- Least Significant Different
dbh	- Diameter at Breast Height
DIP	- Digital Image Processor
CCD	- Charged Coupled Device
FL	- Fibre Lumen
FLU	- Fibre Lumen Diameter
R	- Ray
CW	- Cell Wall
VD	- Vessel Diameter
Ves	- Vessel
FD	- Fibre Diameter
FWT	- Fibre Wall Thickness
magn.	- Magnification

Abstract of thesis submitted to the Senate of Universiti Pertanian Malaysia in fulfillment of the requirements for the degree of Master of Science.

**VARIATION AND RELATIONSHIP OF SELECTED WOOD
PROPERTIES IN PLANTED KELEMPAYAN
(*Neolamarckia cadamba* (Roxb.) Bosser)**

By

ISMAIL JUSOH

Chairman : Assoc. Prof. Mohd. Zin Jusoh

Faculty : Forestry

The tall and straight bole of Kelempayan (*Neolamarckia cadamba* (Roxb.) Bosser), a fast-growing indigenous species, has the potential to be used for forest plantation species. This study was carried out to evaluate the inherent properties of the wood. Six planted trees under similar site conditions were sampled along their radii and at five different height levels to evaluate the inherent variation of wood and the influence of anatomical properties on its specific gravity (SG) and bending strength. Overall means for SG was 0.36, green moisture content 174.83 percent (%), tangential shrinkage 6.46%, radial shrinkage 3.28% and volumetric shrinkage 9.90%. The overall means for modulus of elasticity (MOE) and modulus of rupture (MOR) were 7667 and 71 megapascal (MPa), respectively. Vessel comprised 16.69% of wood, ray 11.96% and fibre 71.41%. Fibre length averaged 1.38 millimeter, fibre diameter 35.01 microns, fibre lumen diameter 24.82 microns and fibre wall thickness 5.11

microns. These physical and mechanical properties are similar to many other light hardwoods species, indicating the suitability of wood for general utility timber.

Significant between-tree variations of wood properties were attributed to genetic and micro-environmental factors, thus enabling selection of genetically superior progeny. Within-tree variations were more consistent in radial than in vertical directions, suggesting that age is a more important factor contributing to the variations than height. Middlewood was more stable dimensionally than innerwood and outerwood.

Significant correlations were recorded among the physical properties, tissue proportions and fibre characteristics. Regression analysis indicated that SG could best be predicted in terms of cell wall proportion, fibre diameter and fibre wall thickness, but the best single predictor was fibre lumen diameter. Bending MOE and MOR were found to be heavily dependent on SG. MOE could best be predicted as a function of SG and ray proportion, whereas the main variables influencing MOR were SG, fibre length and fibre lumen diameter.

The suitability of Kelempayan as general utility timber, established in this study, would be enhanced by further research on its seasoning, processing and machining characteristics.

Abstrak tesis yang dikemukakan kepada Senat Universiti Pertanian Malaysia sebagai memenuhi keperluan untuk Ijazah Master Sains.

**VARIASI DAN PERHUBUNGAN SIFAT KAYU TERPILIH DALAM
KELEMPAYAN (*Neolamarckia cadamba* (Roxb.) Bosser)
YANG DITANAM.**

Oleh

ISMAIL JUSOH

Pengerusi : Prof. Madya Mohd. Zin Jusoh

Fakulti : Perhutanan

Kelampayan (*Neolamarckia cadamba* (Roxb.) Bosser) adalah spesies tempatan yang cepat tumbuh, mempunyai batang yang lurus serta tinggi, berpotensi untuk digunakan sebagai spesies ladang hutan. Kajian ini dijalankan untuk menilai sifat semulajadi kayunya. Enam pokok yang telah ditanam disampel sepanjang jejari dan pada lima ketinggian yang berbeza untuk menilai variasi sifat semulajadi dan pengaruh ciri anatomi terhadap graviti spesifik (SG) dan kekuatan lentur. Pada keseluruhannya min untuk SG ialah 0.36, kandungan lembapan basah 174.83 peratus (%), kecutan tangen 6.46%, kecutan jejari 3.28% dan 9.90% untuk kecutan volumetrik. Min keseluruhan untuk modulus kekenyalan (MOE) dan modulus pecah (MOR) masing-masingnya ialah 7667 dan 71 megapaskal (MPa). Vesel meliputi 16.69% dari keseluruhan kayu, ruji 11.96% dan gentian 71.41%. Purata panjang gentian ialah 1.38 milimeter, diameter gentian 35.01 mikron, diameter lumen gentian 24.82 mikron dan tebal

dinding gentian ialah 5.11 mikron. Sifat fizikal dan mekanikal ini adalah sama dengan kebanyakan spesis kayu keras ringan, menunjukkan kesesuaian kayu ini untuk pelbagai kegunaan am.

Terdapat variasi sifat kayu yang bererti di antara pokok yang disebabkan oleh faktor-faktor genetik dan mikro-persekitaran; dengan ini membolehkan pemilihan progeni yang mempunyai genetik yang baik dibuat. Variasi pada arah jejari dalam sesama pokok adalah lebih konsisten daripada arah tegak, menunjukkan bahawa umur adalah faktor penting yang menyebabkan variasi daripada ketinggian. Dimensi kayutengah adalah lebih stabil daripada kayudalam dan kayuluar.

Korelasi yang bererti telah didapati di antara sifat fizikal, nisbah tisu dan ciri gentian. Analisis regresi menunjukkan SG dapat diramalkan berdasarkan kepada nisbah dinding sel, diameter gentian dan ketebalan dinding gentian tetapi peramal tunggal yang terbaik ialah diameter lumen gentian. MOE dan MOR telah didapati bergantung kuat kepada SG. MOE dapat diramalakan sebagai fungsi SG dan nisbah ruji sementara pembolehubah utama yang mempengaruhi MOR ialah SG, panjang gentian dan diameter lumen gentian.

Kesesuaian Kelempayan sebagai kayu kegunaan am seperti yang telah dikenalpasti oleh kajian ini akan dapat ditambah lagi dengan penyelidikan lanjut mengenai ciri-ciri pengeringan, pemprosesan dan pemesinan.

CHAPTER I

INTRODUCTION

Problem Statement

Kelempayan (*Neolamarckia cadamba* (Roxb.) Bosser) is a fast growing tropical tree species. It grows very well and gregariously in exploited and denuded areas especially after logging. The straight bole and self-pruning characteristics of the tree has attracted attention to the tree as a potentially useful species for tree plantation. The growth characteristics of this tree suggest that under natural regeneration, a dense even-age stand can be formed making it suitable for management as a plantation. The many uses of this tree make it even more attractive to many countries to include this tree in their plantation or reafforestation programmes. Apart from its natural range, this species is already grown as exotics in countries like Western Samoa, Fiji and Puerto Rico (Palmer et al., 1983; Donaldson, 1984; Lugo and Figueroa, 1985).

In its natural distribution, especially in Burma, India and the Philippines, the tree is used for match sticks, poles, pencil slats, carving, wooden shoes, veneer and plywood manufacturing. It has also been used for making cases, furniture and interior finishing. Research has shown that the tree is suitable for pulping

and papermaking for the production of linerboard, bag, wrapping paper and corrugating medium (Peh, 1970; Phillips et al., 1979 and Logan et al., 1984).

Though this tree is found in abundance in Malaysia, it has yet to make its way into the processing mills. Nevertheless as the supplies of the prime natural forest species become scarce and in view of its multiple uses, the future of this tree as a source of raw material is great. The wood industry is expected to rely on considerable portion of the supply of raw materials from this plantation species. In light of this new wood resource which has different characteristics from the prime species, information regarding its characteristics is vital prior to processing.

This tree species is not being utilized because specific knowledge of their properties is inadequate. Studies on the potential utilization of this species should be carried out to investigate whether the wood is desirable for high value products. It appears that considerable information is available on the anatomy, physical and mechanical properties of Kelempayan wood but there is no detailed study on the variation pattern and the relationship between these properties. This study is the first and probably the most intensive of many studies regarding variability of Kelempayan wood and the

influence of anatomical characteristics to its quality and strength.

Objectives

This study is carried out to examine within- and between-tree property variation of Kelempayan wood. The information regarding the anatomy, physical and mechanical properties should be accurately assessed and their variability and relationship determined in order to promote wider utilization. The specific objectives of this study are;

- (1) to describe the physical, mechanical and anatomical properties of Kelempayan wood.
- (2) to evaluate the variation and correlation among the properties found above.
- (3) to determine the relationship between specific gravity and anatomical properties; and
- (4) to determine the relationship of modulus of elasticity and modulus of rupture on specific gravity and anatomical properties.

It is not the intention of this study to determine the best use(s) of the wood but rather to evaluate the inherent characteristics which will have strong bearing on other hardwood species regarding their wood

variability and the relationship between anatomical properties to its physical properties. The information is useful in allocating various parts of the tree as the future resource to appropriate manufacturing processes. The future utilization of this species will undoubtedly reduce the pressure on the need to extract logs from the invaluable forests. This will also result in slowing down the rate of forest exploitation, thus achieving conservation of forest areas.

CHAPTER II

LITERATURE REVIEW

This chapter first present the nomenclature as well as occurrence and distribution of Kelempayan. It then review physical and mechanical properties of the wood, as reported by various researchers. Finally, authors for the quantification of wood anatomy are discussed.

Nomenclature

The tree of this species is known by a variety of vernacular names in accordance to its region of occurrence. It is known as Kelempayan in Peninsular Malaysia (Corner, 1988), kadam in India (Pearson and Brown, 1932), selimpoh in Sarawak (Anderson, 1973) bangkal in Brunei (Browne, 1955) jabon in Indonesia (Mandang et al., 1987), and kaatoan bangkal in the Philippines (Lopez, 1967). In Malaysia the timber is known as laran.

The Kelempayan has gone through a series of changes in its botanical name. Ridley (1923) described the tree as *A. indicus* A. Rich.. Burkill (1935) however called it *Anthocephalus cadamba* (Roxb) miq.. Later Backer and Backhuizen (1965) changed it to *A. chinensis* (Lamk.) Rich. ex Walp.. Bosser (1984) found that the genus *Anthocephalus* is invalid and formally introduced new